

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 074 243 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

07.02.2001 Bulletin 2001/06

(51) Int. Cl.⁷: **A61K 7/48**, C08L 85/02

(21) Application number: **00116065.4**

(22) Date of filing: **27.07.2000**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: **04.08.1999 IT MI991754**

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(72) Inventor: **Pantini, Giovanni**

20100 Milano (IT)

(74) Representative:

Sama, Daniele, Dr.

Sama Patents,

Via G.B. Morgagni, 2

20129 Milano (IT)

(54) **Cosmetic compositions**

(57) Base compositions (premix) comprising the following components:

A) a perfluoropolyether phosphate;

B) a solvent;

C) water.

EP 1 074 243 A2

Description

[0001] The present invention relates to stable, monophasic concentrated compositions containing (per)fluoropolyethers, which are diluted with carriers and excipients in order to be used in the product field for personal care, specifically cosmetic and toilet preparations.

[0002] In particular the formulations of the present invention contain functionalized (per)fluoropolyethers, capable to confer improved protective hydro/oil-repellence properties to the formulation itself. The monophasic formulations of the present invention can be used, after dilution, as cosmetic products for the skin and hair protection towards irritating agents (acids, bases, solvents, detergents) and allergens.

[0003] It is well known in the prior art that (per)fluoropolyethers due to their hydro- and oil-repellence and high filmogenic property are very good protective agents towards both hydrophilic and lipophilic irritating agents.

[0004] It is also known that it is not possible to use (per)fluoropolyethers as such for the personal care and hygiene and that said compounds must be carried in suitable formulations for topic use in order to advantageously utilize the above mentioned properties of (per)fluoropolyethers.

[0005] The (per)fluoropolyether incorporation in polyphase systems in particular under the form of thri-phase emulsions (oil/water/PFPE), used as creams and lotions for skin hydration and protection, is well known. See for example the patents in the name of the Applicant EP 196,904, EP 355,848, EP 390,206. The latter relates to the preparation of concentrated compositions of (per)fluoropolyethers in glycerine in order to facilitate their incorporation in aqueous monophasic systems.

[0006] The (per)fluoropolyethers used in these patents have perfluoroalkyl end groups, which therefore are not reactive end groups.

[0007] The drawback of polyphase systems resides in that they require the presence of two essential components: mineral oils (vegetable, animal or synthetic) and emulsifiers (surfactants). The properties of both these components negatively affect the hydro-repellent and/or oil-repellent action of (per)fluoropolyethers having perfluoroalkyl end groups. Therefore in the thri-phase systems of the prior art the hydro- and oil-repellent properties of (per)fluoropolyethers having perfluoroalkyl end groups are reduced.

[0008] Also in (per)fluoropolyether systems with glycerine good hydro-repellence values are not obtained.

[0009] The thri-phase emulsions are the carrier by which according to the prior art, it is possible to use the above mentioned properties of (per)fluoropolyethers, other systems for formulating compositions having a topic use containing (per)fluoropolyethers, for instance monophasic water-based compositions having hydro- and oil-repellent properties, being not available.

[0010] The need was felt to have available monophasic systems based on perfluoropolyethers having improved hydro- and oil-repellence properties with respect to the known polyphase systems.

[0011] The Applicant has surprisingly and unexpectedly found monophasic concentrated compositions containing functionalized (per)fluoropolyethers, said compositions dilutable with suitable carriers and excipients, in order to obtain products for the personal care, in particular cosmetic and toilet preparations, said cosmetic preparations having a combination of hydro- and oil-repellence properties clearly superior to those of the above described polyphase systems and even superior to those of the pure (per)fluoropolyethers.

[0012] An object of the present invention are therefore concentrated compositions comprising the following components:

A) a (per)fluoropolyether phosphate of general formula:



wherein $l=1$ or 2 ;

- L is a bivalent linking group, preferably of the $(CHR_1CHR_2O)_n$ type wherein R_1, R_2 equal to or different from each other are selected from H, CH_3 ; n is an integer in the range 1-50, preferably 1-6;
- Z_1 equal to or different from Z_2 selected from H, alkaline or ammonium cation, di- or tri-alkanolammonium cation wherein alkanol comprises from 1 to 20 C atoms, preferably 1-4 C atoms, di- or tri- or tetra-alkylammonium cation wherein alkyl comprises from 1 to 20 C atoms, preferably 1-4 C atoms, or $R_f-CF_2CH_2-O-L$;
- R_f is a (per)fluoropolyether chain comprising repeating units selected from one or more of the following ones:

- a) $-(C_3F_6O)-$;
- b) $-(CF_2CF_2O)-$;
- c) $-(CFL_0O)-$, wherein $L_0=F, -CF_3$;
- d) $-CF_2(CF_2)_{z'}CF_2O-$, wherein z' is an integer 1 or 2;




when R_f is monofunctional ($l=1$), an end group is of the perfluoroalkyl type such as for example CF_3O , $\text{C}_2\text{F}_5\text{O}$, $\text{C}_3\text{F}_7\text{O}$; optionally a fluorine atom in the perfluoroalkyl end groups can be substituted by a chlorine or hydrogen atom; examples of these end groups are $\text{Cl}(\text{C}_3\text{F}_6)\text{O}$, $\text{H}(\text{C}_3\text{F}_6\text{O})$;

B) a solvent selected from the following ones: linear or branched when possible alcohols, from 2 to 3 carbon atoms and their methyl ethers; linear or branched glycols from 2 to 6 carbon atoms or linear or branched mono alkylethers wherein the alkyl group ranges from 1 to 4 carbon atoms; dimethoxymethane, known as methylal, acetone;


C) water.

[0013] The preferred compound of general formula (I) is the one wherein Z_1 and Z_2 are different from $R_f\text{-CF}_2\text{CH}_2\text{-O-L-}$; preferably $Z_1 = Z_2 = \text{H}$ and in formula (I) $l = 2$.


[0014] In particular, R_f is of perfluoropolyether type and it has preferably one of the following structures:





with b/a in the range 0.3-10, extremes included, a being an integer different from 0;



wherein z' is an integer equal to 1 or 2;




with $r/b = 0.5-2.0$ $(r+b)/t = 10-30$, b and t being integers different from 0;



R'_f is a fluoroalkylene group from 1 to 4 carbon atoms;

L_0 is selected between F, CF_3 ;



wherein in said formulas:



$-(\text{C}_3\text{F}_6\text{O})-$ can represent units of formula:

$-(\text{CF}(\text{CF}_3)\text{CF}_2\text{O})-$ and/or $-(\text{CF}_2-\text{CF}(\text{CF}_3)\text{O})-$


a, b, b', q', r, t , are integers, whose sum is such that R_f has number average molecular weight \overline{M}_n values in the range of about 300 and about 5,000, and preferably in the range 800-2,500.

The preferred (per)fluoropolyether chain R_f is selected from the following structures:

from the bifunctional ones ($l=2$):




from the monofunctional ones ($l=1$):




wherein L_0 and the a, b, r, t indexes have the above mentioned value, still more preferably $-(\text{CF}_2\text{O})_a-(\text{CF}_2\text{CF}_2\text{O})_b-$.

[0015] The compounds of formula (I) preferably used according to the present invention are those having $L=(\text{CH}_2-\text{CH}_2\text{O})_n$ with $n=1-3$; Z_1 equal to or different from Z_2 is selected from H, NH_4 , or an alkaline metal cation; $l=2$.

[0016] The compounds of general formula (I), having the following formulas, are still more preferred:



wherein $r/a=0.5-2.0$ and $n=1-2$;



wherein $b/a=0.5-3.0$ and $n=1-2$;

wherein a, b and r have the above mentioned meaning.

[0017] The component B) is preferably selected from: ethanol, ethylene glycol, isopropanol, propanol, acetone, methoxyethanol, propylene glycol, propan-1,2-diol, dimethoxy methane, methoxy-isopropanol, diethylene glycol, butan-1,4-diol, diethyleneglycol monoethylether, pentan-1,2-diol, diethyleneglycol monoethylether, dipropylenglycol, dipropylenglycol monomethylether, dipropylenglycol monoethylether; still more preferably: ethanol, isopropanol and propylene glycol.

[0018] In the concentrated composition of the invention the amounts of each of the components A), B) and C) can range from 0.01% to 70% by weight of the composition, preferably from 20% to 40% by weight, the sum of A) + B) + C) being equal to 100% by weight of the composition.

[0019] Still more preferably the concentrated composition contains component A) in a percentage by weight in the range 20%-40%, component B) in the range 30-70% and water component C) in the minimum amount required to obtain a clear solution (the compound of formula (I) as such is insoluble in water), and component C) is generally in the range 5-30% by weight.

[0020] The composition of the invention appears as a monophasic clear solution, stable in the time in environmental conditions at temperatures in the range from 10°C to 35°C also for long periods (6 months or more) of shelf storage.

[0021] Another object of the present invention is a process for preparing said concentrated compositions comprising the following steps:

- solubilization or dispersion with partial solubilization of a (per)fluoropolyether phosphate component A) in component B) at room temperature under mild stirring;
- addition under stirring, to the previous mixture of water component C) initially dropwise, so that component A) is not separated, by dispersing the drop so that the initial appearance of the solution is recovered before adding the subsequent ones, the water aliquots can be increased until the addition is completed, lastly obtaining a clear solution.

[0022] Surprisingly while the (per)fluoropolyether phosphate as such is insoluble in water the mixture of the perfluoropolyether phosphate with component B) is instead dilutable with water to form, as said, a clear solution.

[0023] The added water is preferably at a temperature in the range 50°C-60°C.

[0024] Another object of the present invention is the use of the concentrated compositions of the invention for the preparation of cosmetic compositions under the form of solutions, gels, emulsions, pastes and aerosols or serviettes impregnated with said cosmetic compositions for the skin protection against irritating agents, for the hair protection and treatment, for the protection against sun radiations, for detergency, as deodorants, after-shaves, disinfectants for external use, make-up compositions and for the nail-varnish removal.

[0025] To formulate the cosmetic compositions, the concentrated compositions of the present invention are diluted with the necessary solvents and excipients so that the final percentage by weight of the (per)fluoropolyether phosphate is in the range 0.01-10%, preferably 0.5-5%.

[0026] The concentrated composition can for example be diluted to form a homogeneous solution. In this case the dilution solvent is for example selected from water, acetone, linear or branched alcohols from 2 to 3 carbon atoms and their corresponding methyl ethers; linear or branched glycols from 2 to 6 carbon atoms and their corresponding monoalkylethers wherein the linear or branched ether alkyl group has a number of carbon atoms from 1 to 4; dimethoxymethane.

[0027] Preferably the diluent is water or it is formed by mixtures of water with one or more of the other above mentioned solvents or diluents.

[0028] To said final solution the excipients well known to the skilled man, such as perfumes, dyes, etc., can be added.

[0029] The concentrated composition can also be directly added to an already formulated hydrophilic gel, obtaining protective gels. The hydrophilic gelling agents can for example be selected from polysaccharides, such as cellulose derivatives, xanthan rubber, carruba rubber and alginates; acrylic derivatives, such as carbomer, glyceropolycrylates and polymethacrylates; mineral and synthetic silicates; inorganic salts such as sodium chloride or magnesium sulphate.

[0030] Said protective gels can comprise other ingredients or excipients well known to the skilled man, such as pig-

ments, sun filters, emollient oils (including non functionalized perfluoropolyethers), surfactants.

[0031] The concentrated composition of the present invention can be added to emulsions of the oil/water, or water/oil type or to gel emulsions based on acrylic polymer emulsifiers such as Pemulen® TR-1 or Pemulen® TR-2, obtaining stable emulsions. Said emulsions are considered stable since no separation of phases both after conditioning for 60 days in stove at the temperature of 40°C, and after centrifugation at 4,000 rpm for 10 minutes, occurs.

[0032] Other cosmetic compositions can be prepared by formulating the concentrated composition object of the present invention with suitable carriers and excipients well known to the skilled man in order to obtain soaps, syndet (synthetic soaps) or mixtures thereof; shampoos, preferably containing non ionic and anionic surfactants; tooth pastes.

[0033] For the evaluation of the protective hydro and oil-repellent activity, absorption tests have been carried out on filter paper treated with the concentrated composition of the present invention and of a cosmetic gel formulation obtained by said concentrated composition. See the Examples.

[0034] The (per)fluoropolyethers of general formula (I) are obtainable by the well known processes of the prior art, see for example the following patents herein incorporated by reference: USP 3,665,041, 2,242,218, 3,715,378, and EP 239,123. The functionalized fluoropolyethers having an hydroxyl termination are obtained for example according to EP 148,482, USP 3,810,874.

[0035] The preparation of the monofunctional (per)fluoropolyether phosphates of general formula (I) wherein R_f has a perfluoroalkyl end group can be carried out by reacting the corresponding monohydroxy-terminated (per)fluoroalkylenoxides with POCl₃. A molar ratio POCl₃/hydroxy-terminated compound in the range 2/1-10/1, preferably 6/1-8/1 is used. The reaction is carried out by slowly dropping the monohydroxy-terminated (per)fluoropolyether in POCl₃, at a temperature in the range 50°-100°C, preferably 70°-80°C, by eliminating the HCl vapours in a KOH trap. The POCl₃ excess is removed by distillation while the formed adduct is hydrolized by H₂O. The hydr-olyzed adduct is further reacted for example with an equimolar amount of hydroxy-terminated (per)fluoropolyether to form the ester.

[0036] The separation of the obtained product is carried out by extraction with a suitable organic solvent, such as for example ethyl acetate. From the organic phase the compound of formula (I) is separated according to known techniques, for example by the solvent evaporation.

[0037] The preparation of bifunctional (per)fluoropolyether phosphates (in this case R_f of formula (I) has no perfluoroalkyl end groups) can be carried out by reacting the corresponding di-hydroxy-terminated (per)fluoroalkylenoxides with POCl₃. A molar ratio POCl₃/di-hydroxy-terminated compound in the range 4/1-20/1, preferably 12/1-16/1, is used. The reaction is carried out by slowly dropping the hydroxy-terminated compound in POCl₃, at a temperature in the range 50°-100°C, preferably 70°-80°C, by eliminating the HCl vapours in a KOH trap. The POCl₃ excess is removed by distillation while the formed adduct is hydrolized by H₂O. The separation of the product is carried out by extraction with an organic solvent, such as for example ethyl acetate. From the organic phase the product is separated according to known techniques, for example by solvent evaporation.

[0038] Some examples are reported hereinafter, but they are not limitative of the present invention.

EXAMPLE 1

[0039] 50 g of bifunctional perfluoropolyether phosphate chemically defined as polyperfluoroethoxymethoxydifluoroethyl PEG phosphate (Fomblin® HC/P2-1000), having number average molecular weight of the perfluorinated chain of about 1,000, are solubilized, under slow stirring, in 100 g of ethanol. To this solution 50 g of water, initially drop by drop, are subsequently added, stopping the addition if turbidity appears in the solution and in this case by mixing until turbidity disappears. After few drops, the amount of water which is each time added is increased, maintaining the solution under stirring. At the end a limpid, transparent solution, having the following composition as percentage by weight is obtained:

- Fomblin® HC/P2-1000 (component A) : 25%
- Ethanol (component B): 50%
- water (component C): 25%.

EXAMPLE 2

[0040] One operates as in Example 1, but replacing ethanol with propylene glycol.

[0041] A limpid, transparent solution, having the following composition as percentage by weight is obtained:

- Fomblin® HC/P2-1000 (component A) : 25%
- Propylene glycol (component B): 50%
- water (component C): 25%.

EXAMPLE 3 comparative (comp)

[0042] A concentrated composition is prepared as in Example 1, by mixing component A) with component B), but omitting the addition of component C).

[0043] A limpid solution having the following composition is obtained:

- Fomblin® HC/P2-1000 (component A) : 33.3%
- Ethanol (component B): 66.6%

EXAMPLE 4 comparative (comp)

[0044] 50 g of bifunctional perfluoropolyether having hydroxyl end groups, chemically defined as poliperfluoroethoxy-methoxydifluorohydroxyethyl PEG ether, Fomblin® HC/OH-1000 having a number average molecular weight of the perfluorinated chain of about 1,000, are solubilized in 100 g of ethanol. A transparent solution is obtained, to which 50 g of water are added in aliquots at 50°C under continuous stirring, as indicated in Example 1.

[0045] The composition as percentage by weight is the following:

- Fomblin® HC/OH-1000 (component A) : 25%
- Ethanol (component B): 50%
- water (component C): 25%.

[0046] The immediate separation of the bifunctional perfluoropolyether from the aqueous phase is observed with formation of a lower phase.

[0047] This Example shows that a bifunctional (per)fluoropolyether having hydroxyl end groups cannot be used for preparing the concentrated compositions of the present invention.

EXAMPLE 5

Dilution with water of the concentrated solution according to Example 1.

[0048] One operates as in Example 1, further diluting the obtained composition with water until a final solution having a 3% concentration by weight of Fomblin® HC/P2-1000 is obtained.

[0049] Said solution appears homogeneous and limpid as the starting one. This shows that the concentrated solutions according to the present invention are dilutable by using the previously described solvents.

EXAMPLE 6

Hydro/oil-repellence test on the solutions of Examples 3 (comparative) and 5 and on a non functionalized perfluoropolyether as such.

[0050] 0.5 ml of the solutions of Example 3 (comparative) and of Example 5 have been applied on a filter paper by distributing each of the two liquids on an area of 20 cm². The area is delimited with a marking pen and the paper dried by a hot air flow. A drop of vaseline oil and water respectively are applied on separated parts of the area treated with each solution, measuring the absorption times of the paper.

[0051] The part treated with the solution at 3% by weight of Fomblin® HC/P2-1000 absorbs the water drop in a time higher than 1 hour and the oil drop in a time higher than 6 hours.

[0052] The part treated with the solution of Example 3 (comparative) absorbs the water drop in a time lower than 20 minutes, while for the absorption of the oil drop the results are similar to those above described treating the paper with the diluted solution according to the invention of Example 5.

[0053] The filter paper has been treated with the same above described procedures with the non functionalized perfluoropolyether polyperfluoromethylisopropyl ether Fomblin® HC/04, measuring the hydro-/oil-repellence by the above described procedure. The perfluoropolyether is used pure being it unsoluble either in component B) or in component C) of the composition according to the present invention.

[0054] The absorption times in this case are higher than 1 hour for the water and lower than 20 minutes for the oil.

[0055] This test shows that both a concentrated composition of the perfluoropolyether phosphate wherein water is absent, and a non functionalized perfluoropolyether as such, have not the combination of hydro-repellence and oil-

repellence properties of the diluted compositions of the present inventions.

EXAMPLE 7

5 [0056] One operates as in Example 1, diluting with a mixture water/ethanol so as to obtain a 5% solution by weight of Fomblin[®] HC/P2-1000 and 25% by weight of ethanol. The final solution has pH 2.01 and it appears limpid and homogeneous as the starting one. The pH is then increased of about a pH unit a time, by adding each time some drops of a concentrated NaOH solution, keeping an aliquot of about 100 ml of each solution having the correct pH.

10 [0057] At the end 5 different solutions each having the pH indicated in Table 1, are obtained, in addition to the starting one. On these solutions the hydro-/oil-repellence test is carried out by operating as described in Example 6.

[0058] The results are indicated in Table 1 and show that when the composition of the invention contains alcohol as component B), a good combination of hydro-/oil-repellence properties is obtained at low pH values, to which the perfluoropolyether phosphoric functionality is not neutralized or is only partially neutralized.

15 EXAMPLE 8

Cosmetic composition usable as nail-varnish.

20 [0059] 5 g of diethylenglycol monoethylether and 93 g of acetone are added to 2 g of the concentrated mixture of Example 1. A limpid homogeneous solution, usable as solvent for nail-varnish is obtained, having the following composition (% by weight):

25	- perfluoropolyether phosphate (Fomblin [®] HC/P2-1000)	0.5
	- ethanol	1
	- water	0.5
30	- diethylenglycol monoethylether	5
	- acetone up to	100

EXAMPLE 9

35

Cosmetic composition usable as collutory.

[0060] 2 g of ethanol, 10 g of glycerine, isopropyl methacresol (timol) are added to 2 g of the concentrated mixture of Example 1, adding an amount of water until obtaining 100 g of solution.

40 [0061] The % composition by weight is the following:

45	- isopropyl methacresol (timol)	0.03
	- perfluoropolyether phosphate (Fomblin ^R HC/P2-1000)	0.5
	- ethanol	3.0
	- glycerine	10.0
50	- aroma	as suff.
	- water up to	100

EXAMPLE 10

55

Dilution with water of the concentrated solution of Example 2.

[0062] Starting from the concentrated composition prepared in Example 2, water is added until obtaining a final

solution containing 3% by weight of Fomblin® HC/P2-1000. The solution has pH 2.38 and it appears homogeneous and limpid.

EXAMPLE 11

Cosmetic composition usable as protective gel.

[0063] The concentrated solution of Example 1 is mixed with a gel obtained by adding to Carbomer in powder an amount of water and neutralizing with NaOH. The excipients mentioned hereunder are then added, obtaining the following composition as % by weight:

- Carbomer (Carbopol® Ultrez 10)	1.0
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	5
- ethanol	5.0
- dye CI 42051	0.05
- phenoxyethanol+ methylparaben + propylparaben	0.6
- sodium hydroxide	0.4
- water up to	100

[0064] A blue, transparent gel having pH 5.2 is obtained. The viscosity, measured by a Brookfield DV II viscometer, 10 rpm, at 25°C is 28,000 mPa.s.

[0065] The gel kept in the packing is stable at the shelf storage for times higher than 6 months at room temperature.

EXAMPLE 12

Protective gel.

[0066] A gel is prepared according to the procedure of the previous Example but increasing the ethanol amount from 5% to 25%. The dye is not included in the formulation. The following composition as % by weight is obtained:

- Carbomer (Carbopol® Ultrez 10)	1.2
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	2.0
- ethanol	25.0
- sodium hydroxide	0.45
- water up to	100

[0067] A transparent gel having pH 6.1 and a viscosity, measured as indicated in Example 11, of 45,300 mPa.s, is obtained.

EXAMPLE 13

Protective gel.

[0068] The procedure described in Example 11 is followed, omitting the neutralization and using as gelling excipient xanthan rubber. The obtained composition is the following as percentage by weight:

- xanthan rubber (Rhodicare® T)	1.3
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	5
- ethanol	25.0
- water up to	100

[0069] A transparent gel having pH 2.8 and a viscosity of 13,400 mPa.s measured as described in Example 11, is obtained.

EXAMPLE 14

Hydro-/oil-repellence test on the gel formulations of Examples 11, 12 and 13 respectively.

[0070] The process described in Example 6 is followed, but applying on the paper 0.5 ml of each gel.

[0071] For comparative purpose the commercial cream Decubal® (produced by A/S Dumex of Copenhagen) having a high content of greases (38% by weight) has been used. The obtained results are indicated in Table 2.

[0072] The Table shows that the formulations according to the present invention have better oil-repellent properties than those of the commercial cream, while the hydro-repellent properties are equal or comparable, depending on the type of gel used, even though the composition of the invention contain an amount of the hydrophobic component (perfluoropolyether phosphate) which is about from 1/20 to 1/6 with respect to the total lipophilic (hydrophobic) amount (greases) of the commercial cream.

EXAMPLE 14a

[0073] In order to check whether the hydro-/oil-repellent properties of the cosmetic formulations according to the present invention are kept also under drastic conditions, two different portions of filter paper have been respectively covered with the cosmetic formulations according to Examples 11, 12 and 13 and with the comparative commercial cream, according to the procedure described in Example 6. For each formulation used, one of the two portions of the filter paper is dipped in hot running water at 70°C for 10 minutes, the other one in water containing 0.5% by weight of liquid soap for 10 minutes, at room temperature. After drying, the hydro-/oil-repellent properties are measured as described in Example 6. The results are reported respectively in Tables 3 and 4.

[0074] The Tables show that under the conditions adopted in the test the cosmetic formulations of the invention maintain the hydro-/oil-repellent properties while the hydro-repellence of the commercial cream results lowered.

EXAMPLE 15

Biphasic cosmetic formulation in gel form.

[0075] 100 parts of the gel of Example 11 are added with 3 parts of iron oxides, 3 parts of mica and 3 parts of talc obtaining a coloured gel, which kept in the packing is stable at the shelf storage for times higher than 6 months at room temperature.

EXAMPLE 16

Biphasic cosmetic formulation gel-emulsion.

[0076] 10 g of neopentyl glycol diethylhexanoate are added to 50 g of the gel of Example 11, under continuous stirring. A gel-emulsion is formed which kept in the packing is stable at the shelf storage for times higher than 6 months at room temperature.

EXAMPLE 17Cosmetic formulations of sun cream (gel-emulsion).

5 a) Sun cream with UV filter of chemical type

[0077] One operates as in Example 13, by adding to the base hydroalcoholic solution of perfluoropolyether phosphate (Fomblin® HC/P2-1000) polyperfluoromethylisopropylether (Fomblin® HC/R), UV screening substances of chemical type (butylmethoxybenzoylmethane and octylmethoxycinnamate) and the usual excipients.

10 [0078] A sun gel cream pH = 3.5 having the following composition (% by weight) is obtained:

15	- xanthan rubber (Rhodicare® T)	1.3
	- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	2.0
	- perfluoropolyether (Fomblin® HC/R)	1.0
	- ethanol	30.0
20	- butylmethoxybenzoylmethane	1.0
	- octylmethoxycinnamate	5.0
	- perfume	0.05
25	- water up to	100

b) Sun cream with UV filter of physical type

[0079] One operates as in Example 13 by adding to the concentrated hydroalcoholic solution of perfluoropolyether phosphate (Fomblin® HC/P2-1000), ethyl alcohol, polyperfluoromethylisopropylether (Fomblin® HC/R), an UV screening substance of physical type (titanium dioxide) and the usual excipients.

[0080] A sun gel cream pH = 4.3 having the following composition (% by weight) is obtained:

35	- xanthan rubber (Rhodicare® T)	1.3
	- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	2.0
	- perfluoropolyether (Fomblin® HC/R)	1.0
40	- ethanol	30.0
	- titanium dioxide	2.0
	- perfume	0.05
45	- water up to	100

c) Sun cream with a mixture of UV filters of chemical + physical type

50 [0081] One operates as in Example 13 by adding to the concentrated hydroalcoholic solution of perfluoropolyether phosphate (Fomblin® HC/P2-1000), ethyl alcohol, polyperfluoromethylisopropylether (Fomblin® HC/R), UV screening substances of chemical type (butylmethoxybenzoylmethane and octylmethoxycinnamate), an UV screening substance of physical type (titanium dioxide) and the usual excipients.

[0082] A sun gel cream pH = 4.3 having the following composition (% by weight) is obtained:

55

- xanthan rubber(Rhodicare [®] T)	1.3
- perfluoropolyether phosphate (Fomblin [®] HC/P2-1000)	2.0
- perfluoropolyether (Fomblin [®] HC/R)	1.0
- ethanol	30.0
- butylmethoxybenzoylmethane	1.0
- octylmethoxycinnamate	5.0
- titanium dioxide	2.0
- perfume	0.05
- water up to	100

EXAMPLE 18 comparative (comp)

Preparation of a gel emulsion containing a non functionalized perfluoropolyether and evaluation of the hydro-/oil-repellent properties.

[0083] A gel emulsion with the following formulation has been prepared, wherein as non functionalized perfluoropolyether Fomblin[®] HC/R having number average molecular weight 3,200 and perfluoromethyl end groups has been used.

[0084] The composition in % by weight is the following:

- mineral oil	10
- caprylic/capric triglyceride	5
- perfluoropolyether (Fomblin [®] HC/R)	5
- cetearyl isononanoate	5
- acrylate/alkyl-acrylate (Pemulen [®] TR-1)	0.4
- triethanolamine	0.3
- phenoxyethanol+ methylparaben + propylparaben	0.6
- water up to	100

[0085] The hydro-/oil-repellence test has been carried out as described in Examples 6 and 14. In this case the absorption of the water and vaseline oil drops from the filter paper treated with the emulsion is immediate. Therefore the formulation containing the non functionalized perfluoropolyether has no hydro-/oil-repellent properties.

EXAMPLE 19**Cosmetic formulation shampoo type.**

[0086] The solution at 25% by weight of perfluoropolyether phosphate (Fomblin[®] HC/P2-1000) of Example 2 is added of the following substances:

- surfactants: sodium lauryl ether sulphate (SLES, solution at 30% by weight in water), cocaminopropylbetaine (CAPB, solution at 20% by weight in water) and lauryl polyglucoside (LPG, solution at 20% by weight),
- viscosity improving agent: polyethylenglycol glycerylcocoate with 7 molecules of ethylene oxide (polyethylenglycol (7) glycerylcocoate, PEG-7 GC), obtaining a clear detergent composition pH 9.5 having the following

composition (% by weight):

5

- sodium laurylether sulphate (SLES)	3.5
- cocaminopropylbetaine (CAPB)	1.5
- lauryl polyglucoside (LPG)	5
- polyethylenglycol (7) glycerylcocoate	0.5
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	1
- water up to	100

10

15 EXAMPLE 20

Cosmetic formulation shampoo type.

20 [0087] The previous Example is repeated without adding CAPB and using as viscosity improving agents, instead of polyethylenglycol 7 glycerylcocoate, sodium chloride at 2% by weight in water and polyethylenglycol glyceryl oleate/cocoate with 18 molecules of ethylene oxide (PEG-18-glyceryl oleate/cocoate) at 3% by weight in water. A clear detergent formulation pH 8 having the following composition (% by weight) is obtained:

25

- sodium laurylether sulphate (SLES)	3.5
- lauryl polyglucoside (LPG)	5
- sodium chloride	2
- PEG-18-glyceryl oleate/cocoate	3
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	1
- water up to	100

30

35

EXAMPLE 21

Preparation of a syndet cosmetic formulation.

40 [0088] 3 g of the solution of Example 2 are added to 97 g of the Zetesap® 813A base by Zschimmer & Schwarz, formed for 30-40% by laurylether sodium sulphate and sodium laurylsulphosuccinate, and furthermore containing starch and greasy substances. After gradual homogenization and extrusion a solid syndet is obtained.

EXAMPLE 22

45

Cosmetic formulation Marseille soap type.

[0089] 3 g of the solution of Example 2 are added to 97 g of the base suitable to obtain Marseille soaps, of common commercial availability. After gradual homogenization and extrusion a Marseille soap is obtained.

50

EXAMPLE 23

Cosmetic formulation in fluid emulsion.

55 [0090] The solution of Example 2 is used as the base for preparing a fluid emulsion having the following composition (% by weight):

5

10

15

- stearate of the stearyl ethoxylate alcohol (5)	4
- cetylstearyl ethoxylate alcohol (21)	2
- octyl palmitate	10
- propylene glycol	9
- cetylstearyl alcohol	0.5
- phenoxyethanol + methylparaben + propylparaben	0.8
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	3
- water up to	100

[0091] An emulsion having pH 2.55 and viscosity 10,100 mPa.s, measured as described in Example 11, is obtained. The emulsion kept in the packing is stable at the shelf-storage for times higher than 6 months at room temperature.

20

EXAMPLE 24

Cosmetic formulation gel-emulsion.

25

[0092] The solution of Example 2 is used as the base for preparing a fluid emulsion having the following composition (% by weight):

30

35

40

- acrylate/alkylacrylate polymer Pemulen® TR-2	0.2
- carbomer	0.3
- octyl palmitate	10
- propylene glycol	9
- sodium hydroxide	0.17
- phenoxyethanol + methylparaben + propylparaben	0.8
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	3
- disodium ETDA	0.1
- water up to	100

45

[0093] An emulsion having pH 4.96 and viscosity 9,900 mPa.s, measured as described in Example 11, is obtained. The emulsion kept in the packing is stable at the shelf-storage for times higher than 6 months at room temperature.

EXAMPLE 25

50

Cosmetic formulation water emulsion in oil.

[0094] The solution of Example 2 is used as the base for the preparation of a fluid emulsion having the following composition (% by weight):

55

- vaseline	15
------------	----

(continued)

- cetylstearyl ethoxylate alcohol (21)	1.8
- mineral oil	6
- propylene glycol	9
- cetylstearyl alcohol	7.2
- phenoxyethanol + methylparaben + propylparaben	0.7
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	3
- tocopheryl acetate	0.15
- disodium EDTA	0.12
- citric acid	0.04
- water up to	100

[0095] The obtained emulsion has pH = 2.79 and viscosity 20,800 mPa.s, measured as described in Example 11. The emulsion kept in the packing is stable at the shelf-storage for times higher than 6 months at room temperature.

EXAMPLE 26

Cosmetic formulation in gel having a physiological pH.

[0096] A concentrated composition has been prepared by mixing, according to the procedures described in Example 1, propylene glycol, Fomblin HC/P2-1000 and water so as to obtain the following concentrated composition (percentages by weight):

- Fomblin HC/P2-1000 :	25%
- Propylene glycol :	25%
- water :	50%

[0097] The concentrated composition has been added to a preformed Carbomer gel, prepared as described in Example 11 so as to have the following composition by weight:

- Carbomer (Carbopol® Ultrez 10)	0.2
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	0.5
- propylene glycol	0.5
- phenoxyethanol + methylparaben + propylparaben	0.6
- sodium hydroxide as suff. to	pH 5.4
- water up to	100

[0098] A transparent gel, which kept in the packing is stable at the shelf-storage for times higher than 6 months at room temperature, is obtained.

[0099] On the gel the hydro-/oil-repellence test has been carried out according to Example 6. The results are reported in Table 5.

EXAMPLE 27Cosmetic formulation in gel having a physiological pH.

- 5 **[0100]** By using the concentrated composition prepared in Example 26, three cosmetic formulations are prepared under the form of gels with xanthan rubber, having pH respectively of 4.5, 5.5, and 7

a) Gel pH 4.5

10 **[0101]**

15

20

- xanthan rubber (Rhodicare® T)	0.2
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	2.0
- Propylene glycol	2.0
- Sodium hydroxide as suff. to	pH 4.5
- water up to	100

b) Gel pH 5.5

25 **[0102]**

30

35

- xanthan rubber (Rhodicare® T)	0.2
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	2.0
- Propylene glycol	2.0
- Sodium hydroxide as suff. to	pH 5.5
- water up to	100

c) Gel pH 7

40 **[0103]**

45

50

- xanthan rubber (Rhodicare® T)	0.2
- perfluoropolyether phosphate (Fomblin® HC/P2-1000)	2.0
- Propylene glycol	2.0
- Sodium hydroxide as suff. to	pH 7
- water up to	100

[0104] On these preparations the hydro-/oil-repellence test has been carried out according to Example 6. The results are reported in Table 5.

- 55 **[0105]** The Table shows that by using the concentrated compositions according to the present invention it is possible to prepare cosmetic formulations having a physiological pH, i.e. in the range 4.5 - 7, having a very good combination of hydro-/oil-repellent properties.

Table 1

pH of Fomblin [®] solution	Water absorption times	Oil absorption times
2.01	>1 hour	>6 hours
3.4	>1 hour	>6 hours
4.37	2 minutes	>6 hours
6.8	10 seconds	>6 hours
7.39	5 seconds	>6 hours
8.43	3 seconds	>6 hours

Table 2

Examples	Water absorption times	Oil absorption times
11	>20 minutes	>6 hours
12	>20 minutes	>6 hours
13	>1 hour	>6 hours
Decubal [®] (comp)	>1 hour	immediate

Table 3

Hydro/oilrepellent properties after treatment with water at 70°C		
Examples	Water absorption times	Oil absorption times
11	>1 hour	>6 hours
12	>1 hour	>6 hours
13	>1 hour	>6 hours
Decubal [®] (comp)	20 minutes	immediate

Table 4

Hydro/oilrepellent properties after treatment with water at 0.5% of liquid soap at room temperature		
Examples	Water absorption times	Oil absorption times
11	>1 hour	>6 hours
12	>1 hour	>6 hours
13	>1 hour	>6 hours
Decubal [®] (comp)	20 minutes	immediate

Table 5

Examples	Water absorption times	Oil absorption times
26	>2 hours	>6 hours
27 a)	~4 hours	>6 hours
27 b)	~4 hours	>6 hours
27 c)	~3 hours	>6 hours

Claims

1. Concentrated compositions comprising the following components:

A) a (per)fluoropolyether phosphate of general formula:



wherein $l=1$ or 2 ;

L is a bivalent linking group, preferably of the $(CHR_1CHR_2O)_n$ type wherein R_1, R_2 equal to or different from each other are selected from H, CH_3 ; n is an integer in the range 1-50, preferably 1-6;

Z_1 equal to or different from Z_2 selected from H , alkaline or ammonium cation, di- or tri-alkanolammonium cation wherein alkanol comprises from 1 to 20 C atoms, preferably 1-4 C atoms, di- or tri- or tetra-alkylammonium cation wherein alkyl comprises from 1 to 20 C atoms, preferably 1-4 C atoms, or $R_f-CF_2CH_2-O-L$; R_f is a (per)fluoropolyether chain comprising repeating units selected from one or more of the following ones:

a) $-(C_3F_8O)-$;

b) $-(CF_2CF_2O)-$;

c) $-(CFL_0O)-$, wherein $L_0=F, -CF_3$;

d) $-CF_2(CF_2)_{z'}-CF_2O-$, wherein z' is an integer 1 or 2;

e) $-CH_2CF_2CF_2O-$;

when R_f is monofunctional ($l=1$), an end group is of the perfluoroalkyl type selected from CF_3O, C_2F_5O, C_3F_7O ; optionally a fluorine atom in the perfluoroalkyl end groups is substituted by a chlorine or hydrogen atom;

B) a solvent selected from the following ones: linear or branched alcohols from 2 to 3 carbon atoms and their corresponding methyl ethers; linear or branched glycols from 2 to 6 carbon atoms and their corresponding mono alkylethers wherein the linear or branched ether alkyl group comprises from 1 to 4 carbon atoms; dimethoxymethane acetone;

C) water.

2. Compositions according to claim 1, wherein in the compound of general formula (I) Z_1 and Z_2 are different from $R_f-CF_2CH_2-O-L$; preferably $Z_1 = Z_2 = H$ and $l = 2$.
3. Compositions according to claims 1-2, wherein R_f is of (per)fluoropolyether type and it is preferably selected from one of the following structures:

1) $-(CF_2O)_a-(CF_2CF_2O)_b-$

with b/a in the range 0.3-10, extremes included, a being an integer different from 0;

2) $-(CF_2-(CF_2)_{z'}-CF_2O)_b-$

wherein z' is an integer equal to 1 or 2;

- 3) $-(C_3F_6O)_r-(C_2F_4O)_b-(CFL_0O)_t-$,
 with $r/b = 0.5-2.0$ $(r+b)/t = 10-30$, b and t being integers different from 0;
 4) $-(OC_3F_6)_r-(CFL_0O)_t-OCF_2-R_f-CF_2O-(C_3F_6O)_r-(CFL_0O)_t-$
 5) $-(CF_2CF_2CH_2O)_q-R_f-O-(CH_2CF_2O)_q-$ wherein:

R_f is a fluoroalkylene group from 1 to 4 carbon atoms;
 L_0 is selected between F, CF_3 ;


- 6) $-(C_3F_6O)_r-OCF_2-R_f-CF_2O-(C_3F_6O)_r-$ wherein in said formulas:

$-(C_3F_6O)-$ can represent units of formula:

$-(CF(CF_3)CF_2O)-$ and/or $-(CF_2-CF(CF_3)O)-$

and a, b, b', q, r, t , are integers, whose sum is such that R_f has number average molecular weight \overline{M}_n values in the range of about 300 and about 5,000, and preferably in the range 800-2,500.

4. Compositions according to claim 3, wherein the (per)fluoropolyether chain R_f is selected from the following structures:




wherein L_0 and the a, b, r, t indexes have the above mentioned value.


5. Compositions according to claims 3 and 4, wherein the perfluoropolyether chain R_f is $-(CF_2O)_a-(CF_2CF_2O)_b-$ and the a and b indexes are as above indicated.

6. Compositions according to claims 1-6, wherein the compounds of formula (I) are those having $L=(CH_2-CH_2O)_n$ with $n=1-3$; Z_1 equal to or different from Z_2 is selected from H, NH_4 , or an alkaline metal cation; $l=2$.

7. Compositions according to claims 1-5, wherein the component A is a (per)fluoropolyether having the following formulas:



wherein $r/a=0.5-2.0$ and $n=1-2$;



wherein $b/a=0.5-3.0$ and $n=1-2$;

wherein a, b and r have the above mentioned meaning.

8. Compositions according to claims 1-7, wherein component B) is selected from: ethanol, ethylene glycol, isopropanol, propanol, acetone, methoxyethanol, propyleneglycol, propan-1,2-diol, dimethoxy methane, methoxy-isopropanol, diethylene glycol, butan-1,4-diol, diethyleneglycol monoethylenether, pentan-1,2-diol, diethylen-glycol monoethylether, dipropyleneglycol, dipropyleneglycol monomethylether, dipropyleneglycol monoethylether; still more preferably: ethanol, isopropanol and propylene glycol.

9. Compositions according to claims 1-8, wherein the amounts of each of the components A), B) and C) range from 0.01% to 70% by weight, preferably from 20% to 40% by weight, the sum of A) + B) + C) being the 100% by weight of the composition.

10. Compositions according to claim 9, wherein the percentage by weight of component A) is in the range 20%-40%, that of component B) in the range 30-70% and water in the range 5-30%.

11. A process for preparing concentrated compositions according to claims 1-11, comprising the following steps:

- solubilization or dispersion with partial solubilization of a (per)fluoropolyether phosphate component

A) in component B) at room temperature under mild stirring;

- addition under stirring, to the previous mixture, of water component C) initially dropwise, so that component A) is not separated from the solvent, dispersing the drop so that the initial appearance of the solution is recovered before adding the subsequent ones, the water aliquots are gradually increased until the addition is completed, obtaining a limpid solution.

5

12. Cosmetic compositions comprising the concentrated compositions according to claims 1-10, said cosmetic compositions being under the form of solutions, gels, emulsions, pastes and aerosols for the skin protection against irritating agents, for the hair protection and treatment, for the protection against sun radiations, for detergency, as deodorants, after-shaves, disinfectants for external use, make-up compositions and for the nail-varnish removal.

10

13. Compositions according to claim 12 containing the perfluoropolyether phosphate of formula (I) component a) in a percentage by weight in the range 0.01-10%, preferably 0.5-5%.

15

14. Compositions according to claim 13, wherein the concentrated composition is additived with a diluent selected from water, acetone, linear or branched alcohols from 2 to 3 carbon atoms and their corresponding methyl ethers; linear or branched glycols from 2 to 6 carbon atoms and their corresponding monoalkylethers wherein the linear or branched ether alkyl group has a number of carbon atoms from 1 to 4; dimethoxymethane.

20

15. Compositions according to claim 14, wherein the diluent is water or mixtures formed by water with one or more of the other diluents indicated in claim 14.

16. Compositions according to claims 12-15, under the form of hydrophilic gels.

25

17. Compositions according to claim 16, wherein the hydrophilic gelling agents are selected from: polysaccharides, preferably cellulose derivatives, xanthan rubber, carruba rubber and alginates; acrylic derivatives, preferably carbomer, glyceropolyacrylates and polymethacrylates; mineral and synthetic silicates; inorganic salts preferably sodium chloride or magnesium sulphate.

30

18. Compositions according to claims 16-17 comprising other ingredients such as pigments, sun filters, emollient oils (including non functionalized perfluoropolyethers), surfactants.

19. Compositions according to claims 12-15 under the form of soaps, syndet (synthetic soaps) or mixtures thereof; shampoos, preferably containing non ionic and anionic surfactants; and tooth pastes.

35

20. Compositions according to claims 12-15 under the form of preformed emulsions of the oil/water, water/oil type and gel emulsions based on acrylic polymer emulsifiers such as Pemulen® TR-1 or Pemulen® TR-2.

40

45

50

55

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 074 243 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
18.04.2001 Bulletin 2001/16

(51) Int. Cl.⁷: **A61K 7/48**, C08L 85/02,
C08J 3/02, C08G 65/22,
C08G 65/00, A61K 7/06

(43) Date of publication A2:
07.02.2001 Bulletin 2001/06

(21) Application number: **00116065.4**

(22) Date of filing: **27.07.2000**

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: **04.08.1999 IT MI991754**

(71) Applicant: **Ausimont S.p.A.**
20121 Milano (IT)

(72) Inventor: **Pantini, Giovanni**
20100 Milano (IT)

(74) Representative:
Sama, Daniele, Dr.
Sama Patents,
Via G.B. Morgagni, 2
20129 Milano (IT)

(54) **Cosmetic compositions**

(57) Base compositions (premix) comprising the following components:

- A) a perfluoropolyether phosphate;
- B) a solvent;
- C) water.

EP 1 074 243 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 6065

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.CI.7)
X	EP 0 890 356 A (INTERCOS ITALIANA) 13 January 1999 (1999-01-13) * page 2, line 41 - line 45 * * claims 1-3; examples 2,3 *	1	A61K7/48 C08L85/02 C08J3/02 C08G65/22 C08G65/00 A61K7/06
A	US 4 536 444 A (SUMIYA KENJI ET AL) 20 August 1985 (1985-08-20)		
A	PATENT ABSTRACTS OF JAPAN vol. 016, no. 575 (C-1011), 15 December 1992 (1992-12-15) & JP 04 225075 A (KOSE CORP), 14 August 1992 (1992-08-14) * abstract *		
D,A	EP 0 196 904 A (AUSIMONT SPA) 8 October 1986 (1986-10-08)		
D,A	EP 0 355 848 A (AUSIMONT SRL) 28 February 1990 (1990-02-28)		
D,A	EP 0 390 206 A (AUSIMONT SRL) 3 October 1990 (1990-10-03)		
D,A	US 3 665 041 A (SIANESI DARIO ET AL) 23 May 1972 (1972-05-23)		
D,A	US 3 715 378 A (PASETTI A ET AL) 6 February 1973 (1973-02-06)		
D,A	EP 0 239 123 A (AUSIMONT SPA) 30 September 1987 (1987-09-30)		
D,A	EP 0 148 482 A (DAIKIN IND LTD) 17 July 1985 (1985-07-17)		
D,A	US 3 810 874 A (MITSCH RONALD ALLEN ET AL) 14 May 1974 (1974-05-14)		
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		27 February 2001	Stienon, P
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 6065

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-02-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0890356 A	13-01-1999	IT MI971602 A	07-01-1999
		US 6004541 A	21-12-1999
US 4536444 A	20-08-1985	JP 60109028 A	14-06-1985
		DE 3441981 A	30-05-1985
		GB 2150860 A,B	10-07-1985
JP 04225075 A	14-08-1992	JP 3073240 B	07-08-2000
EP 0196904 A	08-10-1986	IT 1183530 B	22-10-1987
		AT 77400 T	15-07-1992
		AU 592553 B	18-01-1990
		AU 5536286 A	02-10-1986
		BR 8601331 A	02-12-1986
		CA 1276561 A	20-11-1990
		DE 3685675 A	23-07-1992
		DE 3685675 T	14-01-1993
		DE 196904 T	07-04-1988
		ES 553434 D	01-06-1987
		ES 8706185 A	16-08-1987
		JP 1996514 C	08-12-1995
		JP 7008332 B	01-02-1995
		JP 61234928 A	20-10-1986
		MX 162555 A	22-05-1991
		US 4803067 A	07-02-1989
		ZA 8602391 A	26-11-1986
EP 0355848 A	28-02-1990	IT 1229483 B	03-09-1991
		AT 103322 T	15-04-1994
		AU 617212 B	21-11-1991
		AU 4024389 A	01-03-1990
		BR 8904260 A	10-04-1990
		CA 1319579 A	29-06-1993
		DE 68914062 D	28-04-1994
		DE 68914062 T	14-07-1994
		ES 2061841 T	16-12-1994
		JP 2163199 A	22-06-1990
		JP 2633361 B	23-07-1997
		MX 169861 B	28-07-1993
		US 4959171 A	25-09-1990
		ZA 8906405 A	27-03-1991
EP 0390206 A	03-10-1990	IT 1229222 B	26-07-1991
		AT 143033 T	15-10-1996
		AU 624491 B	11-06-1992
		AU 5247390 A	04-10-1990

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 6065

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-02-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0390206 A		BR 9201052 A	28-09-1993
		CA 2013669 A	02-10-1991
		DE 69028564 D	24-10-1996
		DE 69028564 T	30-01-1997
		ES 2094126 T	16-01-1997
		JP 2880239 B	05-04-1999
		JP 3095262 A	19-04-1991
		KR 146054 B	17-08-1998
		US 5562911 A	08-10-1996
		US 5183589 A	02-02-1993
		US 5330681 A	19-07-1994
		ZA 9002443 A	30-01-1991
US 3665041 A	23-05-1972	BE 713178 A	03-10-1968
		CH 517801 A	15-01-1972
		DE 1770126 A	04-11-1971
		FR 1585601 A	30-01-1970
		NL 6804754 A, B	07-10-1968
		SE 342461 B	07-02-1972
US 3715378 A	06-02-1973	DE 1745169 A	05-08-1971
		FR 1574703 A	18-07-1969
		JP 50028409 B	16-09-1975
		US 4451646 A	29-05-1984
EP 0239123 A	30-09-1987	IT 1188635 B	20-01-1988
		AT 89428 T	15-05-1993
		AU 601174 B	06-09-1990
		AU 7053787 A	01-10-1987
		CA 1284989 A	18-06-1991
		CN 87102398 A, B	07-10-1987
		CS 8702125 A	10-02-1989
		DE 3785784 A	17-06-1993
		DE 3785784 T	16-09-1993
		JP 2589080 B	12-03-1997
		JP 62270019 A	24-11-1987
		KR 9600823 B	13-01-1996
		US 5382614 A	17-01-1995
		ZA 8702071 A	14-09-1987
EP 0148482 A	17-07-1985	JP 1497026 C	16-05-1989
		JP 60202122 A	12-10-1985
		JP 63043419 B	30-08-1988
		JP 1060170 B	21-12-1989
		JP 1574231 C	20-08-1990
		JP 61113616 A	31-05-1986

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 00 11 6065

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-02-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0148482 A		JP 1483650 C	27-02-1989
		JP 60137928 A	22-07-1985
		JP 63032812 B	01-07-1988
		CA 1259443 A	12-09-1989
		DE 3485616 A	07-05-1992
		DE 3486428 D	13-06-1996
		DE 3486428 T	10-10-1996
		EP 0415462 A	06-03-1991
		KR 8800659 B	20-04-1988
		SU 1806149 A	30-03-1993
		RU 2107074 C	20-03-1998
		US 4973742 A	27-11-1990
		US 4845268 A	04-07-1989
		RU 2073692 C	20-02-1997
US 3810874 A	14-05-1974	CA 960222 A	31-12-1974
		CA 960221 A	31-12-1974
		CA 960400 A	31-12-1974
		GB 1309401 A	14-03-1973
		US 3845051 A	29-10-1974
		AU 462798 B	10-07-1975
		AU 3317471 A	15-03-1973
		AU 469118 B	05-02-1976
		AU 3317671 A	15-03-1973
		BE 772308 A	07-03-1972
		BE 772309 A	07-03-1972
		DE 2145174 A	23-03-1972
		DE 2145176 A	16-03-1972
		FR 2106375 A	05-05-1972
		FR 2116364 A	13-07-1972
		GB 1373931 A	13-11-1974
		GB 1373932 A	13-11-1974
		IT 939387 B	10-02-1973
		IT 939388 B	10-02-1973
		JP 1408932 C	24-11-1987
		JP 59191721 A	30-10-1984
		JP 62014169 B	01-04-1987
		JP 1408933 C	24-11-1987
		JP 59191722 A	30-10-1984
		JP 62014170 B	01-04-1987
		JP 60034924 A	22-02-1985
		JP 59191723 A	30-10-1984
		JP 1408934 C	24-11-1987
		JP 59191724 A	30-10-1984
		JP 62014171 B	01-04-1987
		JP 1322347 C	11-06-1986

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 6065

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

27-02-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3810874 A		JP 59191725 A	30-10-1984
		JP 60050823 B	11-11-1985
		JP 59030724 B	28-07-1984
		JP 51002083 B	23-01-1976
		JP 1509565 C	26-07-1989
		JP 62048724 A	03-03-1987
		JP 63061336 B	29-11-1988
		NL 7111865 A	10-03-1972
		NL 7112315 A,B	10-03-1972
		US 4094911 A	13-06-1978
		US 3972856 A	03-08-1976
		US 4085137 A	18-04-1978
		BE 747087 A	09-09-1970
		CA 960397 A	31-12-1974
		DE 2011774 A	17-09-1970
		DE 2066042 B	22-11-1979
		FR 2037807 A	31-12-1970
		GB 1309402 A	14-03-1973
		NL 7002813 A,B,	14-09-1970

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82